

Medium/Firm Density

Compression/Deflection, ASTM D 1056-91 2C3/4

Specimens deflection 25% ad 0.5 in/min.

	Results	Requirements	Pass/Fail
Load to Deflect 25%, psi	11.5	9 to 13	Pass

Heat Aged Compression /Deflection, ASTM D 1056-91

Test Method : ASTM D 573-88

Specimens aged 7 days @ 158 °F in a forced air oven

Compression/Deflection, % change	+11.5	+/- 30	Pass
----------------------------------	-------	--------	------

Compression Set, ASTM D 395-89 (94) Method B

Specimens aged 22 hrs. @ RT, 50% deflection 24 hr. recovery

Compression Set, %	9.2	25 max	Pass
--------------------	-----	--------	------

Water Absorption, ASTM D 1056-91 2C3

1" x 4" specimens immersed for 3 min. under 2.5 psi. absolute pressure, then 3 min. In water at atmospheric pressure.

Weight change, %	+0.697	5 max	Pass
------------------	--------	-------	------

Temperature Range - 65°F to 250 °F

Disclaimer

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Cor MFG cannot anticipate all variations in actual end-use conditions Cor MFG makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.